



InvariMatte® Walnut

Product Description

InvariMatte® Walnut is a directional, uniformly textured stainless steel finish with dull bead blast appearance and a thin brownish-black oxide film designed for use in architectural applications. It can be applied to wall panels, column covers, coping and trim. The brownish black chromium oxide film is produced electrochemically. Unlike paint coatings, the finish is not reactive to ultraviolet light. InvariMatte® Walnut retains the corrosion resistance of the underlying ATI 2003 alloy.

Pounds Per Piece

Thickness (in.) x Width (in.) x Length (in.) x .292

Available Sizes

Please refer to Table II. Cut lengths up to 96” are available. (Please note that hanger holes or gripper marks within 3/4” of one long edge of each sheet can be expected.)

Table II	Size Range (inches)				
	WIDTH				
THICKNESS	.75 – 18	>18 <24	24 – 36	>36 – 48	>48 - 60
.075 - .1250	•	•	•	•	
.0291 - .075	•	•	•	•	

Table I	ATI 2003™
CHEMICAL ANALYSIS	
Nickel	3%
Chromium	19.5%
Molybdenum	1.5%
TYPICAL MECHANICAL PROPERTIES	
Yield Strength (psi)	90,000
Tensile Strength (psi)	115,000
Elongation in 2 inches	24%
Hardness (Rockwell B)	23
PHYSICAL PROPERTIES	
Density (lb./cu. in.)	.279
Modulus of Elasticity in Tension (x 10 ⁶ lb./sq. in.)	27.5
Mean Coefficient of Thermal Expansion 72-212 °F (x 10 ⁻⁶ in/in/°F)	7.2

Fabrication

InvariMatte® Walnut is readily welded or soldered. However, exposure to high temperatures will destroy the brownish black oxide film. Once destroyed, the film cannot be repaired. In the case of welding, a grade of welding wire more noble than the work piece should be used. While formation of a heat tint scale can be avoided in lighter gauges through use of shield gasses, care must be taken to remove this scale through chemical means, preferably a phosphoric acid pickling paste (avoid hydrochloric). Since welding will destroy the brownish black oxide film in the heat-affected zone of the weld, the design should provide for concealed welds and joints that are either open or sealed by means of soldering.

In the case of soldering, it is necessary to remove the oxide film in the area of the solder joint. It is also advisable to use low temperature tin/lead soldering practices and avoid chloridecontaining fluxes. Flux residue must be thoroughly removed after soldering.

Fire Resistance

Since stainless steel is dimensionally stable up to 2000°F, InvariMatte® Walnut provides an added measure of protection in the event of a fire.

Flatness

InvariMatte® Walnut is supplied to ASTM (American Society for the Testing of Materials) commercial tolerances.

Installation

Since there is a degree of variability in the appearance of the finish from batch to batch, we recommend establishing an installation technique, similar to the way shingle roofs are installed, whereby the installer works from a few different crates of panels on the job site, so as to distribute panels with certain finish attributes over a wide area, co-mingled with panels made from other sheets.

InvariMatte® Walnut is shipped with a high-grade UV resistant protective plastic covering designed to withstand the elements for several weeks. However, it is advisable to remove this material promptly after installation to prevent adhesive residue from remaining on the colorized stainless steel finish. After installation is completed, any rust stains from tools or construction debris must be removed.

Maintenance

Designed to require very little maintenance, InvariMatte® Walnut is durable and requires only periodic attention. It may, however, be appropriate to clean the surface to maintain its original appearance. Any detergent/ammonia solution can be effective for general cleaning. More tenacious contaminants, like adhesive residue will respond to pure acetone. Chloridecontaining products must be avoided. Areas where incidental debris can collect, such as gutters, must be cleaned on a regular basis. For more information, please refer to “Cleaning Stainless Steel Finishes” in the Resources section of our website at www.metalresources.net.

Warranty

For warranty information, please contact a representative.